



Modkraft

TİPİK DEĞERLER

TEST	Metot	Birim	MODKRAFT					
Gramaj	T 410	g/m ²	110	115	120	125	135	140
Rutubet	T 412	%	8,0	8,0	8,0	8,0	8,0	8,0
Patlama	T 403	kPa	264	270	276	286	317	322
Patlama indeksi	T 403	kPa.m ² /g	2,40	2,35	2,30	2,30	2,35	2,30
Cobb60 üst	T 441	g/m ²	35	35	35	35	35	35

GARANTİ EDİLEN DEĞERLER

TEST	Metot	Birim	Tolerans	MODKRAFT					
Gramaj	T 410	g/m ²	% ± 4	110	115	120	125	135	140
Rutubet	T 412	%	± 1,5	8,0	8,0	8,0	8,0	8,0	8,0
Patlama	T 403	kPa	min	253	265	264	275	297	308
Patlama indeksi	T 403	kPa.m ² /g	min	2,3	2,3	2,2	2,2	2,2	2,2
Cobb60 üst	T 441	g/m ²	± 15	40	40	40	40	40	40

Test Şartları 23±1°C, 50% ± 2% RH

ISO 9001:2015
ISO 14001:2015
ISO 45001:2018
ISO 50001:2018
TS 12728



*Yumurta ve sebze-meyve viollerinde direkt gıda ile temasına uygundur.
İşletme Kayıt No:TR-59-K-016501